

Offshore structural plates



Quality	Y20 Rev 6 (S355MLO)
Standard	Norsok M-120: 2021
Certification	3.2 EN10204
Heattreatment	Thermomechanical rolled

Mechanical properties

Thickness in mm	Min. Yield (Mpa)	Tensile strength (Mpa)	Min. Elongation (%)	Min. Impact Energy (KV J Transverse) -40°
>3 <= 16	355	470 - 630	22	50
> 16 <= 25	355	470 - 630	22	50
> 25 <= 40	345	470 - 630	22	50
>40 <= 63	335	470 - 630	22	50
>63 <= 80	325	470 - 630	22	50
>80 <= 120	325	470 - 630	22	50

Chemical composition

C/ (mm) max.	C/ (mm) max.	C/ (mm) max.	Si max.	Mn max.	P max.	S max.	Cr max.	Ni max.	Mo max.	N max.	Al tot c max.	Cu max.	Nb max.	Ti max.	V max.	Nb+ V max.	Nb+V+Ti max.
<= 16 mm	>16 <=40 mm	>40 mm															
0.12	0.12	0.12	0.550	<= 2,0%	0.020	0.010	0.250	<= 1,0	0.080	0.010	0,015 to 0,055	0.30	0.05	0.025	0.060	0.06	0.08

Maximum

CEV:

PCM:

t <= 75	0.39	0.21
75 < t <= 120	0.40	0.22

Z35 test

t >= 15mm

