

Offshore structural plates



Quality	S460MLO
Standard	EN 10225-1
Certification	3.2 EN10204
Heattreatment	Thermomechanical rolled

Mechanical properties

Thickness in mm	Min. Yield (Mpa)	Tensile strength (Mpa)	Min. Elongation (%)	Min. Impact Energy (KV J Transverse) -40°
>3 <= 16	460	520 - 700	17	60
> 16 <= 25	440	520 - 700	17	60
> 25 <= 40	420	520 - 700	17	60
>40 <= 63	415	500 - 675	17	60
>63 <= 80	405	500 - 675	17	60
>80 <= 120	400	500 - 675	17	60

Chemical composition

C/ (mm) max.	C/ (mm) max.	C/ (mm) max.	Si max.	Mn max.	P max.	S max.	Cr max.	Ni max.	Mo max.	N max.	Al tot c max.	Cu max.	Nb max.	Ti max.	V max.	Nb+ V max.	Nb+V+Ti max.
<= 16 mm	>16 <=40 mm	>40 mm															
0.14	0.14	0.14	0.550	1.700	0.020	0.010	0.250	0.700	0.250	0.010	0.015 to 0,055	0.30	0.05	0.025	0.080	0.12	0.13

Maximum

CEV:

PCM:

t <= 75	0.43	0.22
75 < t <= 120	0.43	0.22

Z35 test

t >= 15mm

